



C3100 - Exterior Latex Flat

Technical Specifications

PRODUCT DESCRIPTION

C3100 ProSeries Exterior Latex Flat is a pure acrylic finish for application in most residential or commercial environments. C3100 ProSeries is specifically formulated to provide maximum coverage, tenacious adhesion and long term weatherability.

SPECIFICATIONS

Type:	Pure Acrylic	Dry Time – Touch:	30 minutes
Sizes:	1's and 5's	Dry Time – Recoat:	2 to 4 hours
Bases:	White, Pastel, Midtone, Accent	Full Service:	14 days
Gloss:	2 to 5% @ 60° 6 to 12% @ 85°	Flash Point:	None
		VOC:	74 grams/liter.
		% Solids Vol:	33 – 35
		Weight Per Gallon:	10.83 +/- .25 lbs.

PRODUCT USE

Surface Preparation

Clean surface to remove contaminants such as dirt, dust, oil, grease, wax, and rust. Remove mildew using a bleach solution of 1 part bleach to 4 parts water. Patch holes and cracks, sand smooth and remove sanding dust.

New Wood: Spot prime all knots and sappy areas with C² ProSeries Exterior Alkyd Primer. Allow primed areas to dry and sand until smooth. Apply one coat of C² ProSeries Exterior Latex Primer to entire surface. If required, sand knots again and remove dust. Finish with one or two coats of C² ProSeries Exterior Latex Flat. Note: For tannin containing woods, best results are achieved by priming with C² ProSeries Exterior Alkyd Primer.

Painted Surfaces: Remove all loose or peeling paint. Dull glossy surfaces. Prime entire surface as required using C² ProSeries Exterior Latex Primer. Finish with one or two coats of C² ProSeries Exterior Latex Flat.

Galvanized Metal: Clean surface with a high solvency thinner. Prime using C² ProSeries Exterior Latex Primer. Finish with one or two coats of C² ProSeries Exterior Latex Flat.

Aluminum/Vinyl Siding: Clean surface using a pressure washer. Finish with one or two coats of C² ProSeries Exterior Latex Flat. Note: Never use dark colors on aluminum or vinyl siding.

Masonry Surfaces: New masonry must be fully cured (90 days). For existing masonry, use pressure washer to remove chalked and peeling paint. Finish with one or two coats of C² ProSeries Exterior Latex Flat.

Application

C3100 ProSeries Exterior Latex Flat may be applied by roller (no less than 3/8-inch nap), brush (synthetic) or spray.

Spreading Rate: Product should be applied at a rate of 400 to 450 square feet per gallon. (37 to 42 square meters per 3.78 liters)

Thinning: Do not thin.

Airless Spray: Use a 12 to 15 mil size tip.

Cleanup: Clean painting equipment and spills immediately using warm, soapy water.

Limitations: Do not apply if product, air or surface temperature is below 50° F (10° C) - Keep product from freezing. Product application and surface conditions are beyond the manufacturer's control. Liability, if any, is limited to replacement of product only.

Disposal: Do not dispose of any paint product or solvent in drains, sewers or municipal garbage. Use all of the paint you purchase or give it to someone who can use it. If disposal is necessary, contact your local municipality.

C² ProSeries Paint is formulated without lead or mercury



C3100 - Exterior Latex Flat Technical Specifications

Last Update – July 22, 1999. (Spec C3100)